

Designed Specifically for Digitally-Printed Labels

2100DL

Clear Polypropylene
Digital Overlamine

2106DL

Matte Polypropylene
Digital Overlamine



| | Finish | Total Thickness (mil) | Film Thickness (mil) | Adhesive | Tensile Strength* | Elongation* | Peel Adhesion** |
|---------------|--------|-----------------------|----------------------|------------------|-------------------|-------------|-----------------|
| 2100DL | Clear | 1.20 | 0.70 | Acrylic Emulsion | 14 | 150 | 18.5 |
| 2106DL | Matte | 1.40 | 1.00 | | 22 | 160 | 18 |

*Tensile/Elongation: PSTC-131 - ASTM D3759

**Peel Adhesion: PSTC-101 - ASTM D3330

The World Leader of Overlamination



SEKISUI TA INDUSTRIES, LLC

Subsidiary of the Sekisui Chemical Co. LTD., Japan

6131 Knott Avenue, Buena Park, CA 90620 Tel: (800) 258-8273 Fax: (714) 990-6851

www.sekisui-ta.com

Certified to ISO 14001: 2004